



TNEMEC PRIMERS SERIES V10

PRODUCT PROFILE

GENERIC DESCRIPTION Modified Alkyd

COMMON USAGE Chemically active, rust-inhibitive primer for ferrous metals. This low VOC primer provides extended weathering for shop and field priming of structural and miscellaneous steel. Series 10-99W can also be used as a primer for wood substrates.

COLORS 99 Red, 1009 Gray, 99G Green, 99B Black, 99W White. **Note:** Minimum order quantities apply for 99G Green and 99B Black.

PERFORMANCE CRITERIA Extensive test data available. Contact your Tnemec representative for specific test results.

COATING SYSTEM

TOPCOATS Series 2H, 2HS, 30, 82HS, 113, 114, 115, 1026, 1028, 1029. **Note:** Some systems are not for use on surfaces that are continually wet or sweat frequently. Reference the applicable topcoat data sheet for additional information.
Note: Series V10 must cure three days before topcoating with Series 1026, 1028 or 1029.

SURFACE PREPARATION

STEEL SSPC-SP2 Hand Tool or SSPC-SP3 Power Tool Cleaning
 SSPC-SP6/NACE 3 Commercial Blast Cleaning when extended field exposure is expected.

WOOD Clean and dry.

ALL SURFACES Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS 58 ± 2.0%

RECOMMENDED DFT 2.0 to 3.5 mils (50 to 90 microns) per coat.

CURING TIME

Temperature	To Touch	Dry Through	To Recoat
75°F (24°C)	30 minutes	4-6 hours	12-16 hours

Curing time varies with surface temperature, air movement, humidity and film thickness.

VOLATILE ORGANIC COMPOUNDS **Unthinned:** 2.74 lbs/gallon (328 grams/litre)
Thinned 1%: 2.74 lbs/gallon (328 grams/litre)

HAPS **Unthinned:** 0 lbs/gal solids
Thinned 1%: 0 lbs/gal solids

THEORETICAL COVERAGE 930 mil sq ft/gal (22.8 m²/L at 25 microns). See APPLICATION for coverage rates.

NUMBER OF COMPONENTS One

PACKAGING 55 gallon (208.2 L) drums, 5 gallon (18.9L) pails and 1 gallon (3.79L) cans.

NET WEIGHT PER GALLON 12.76 ± 0.35 lbs (5.13 ± .16 kg) †

STORAGE TEMPERATURE Minimum 20°F (-7°C) Maximum 110°F (43°C)

TEMPERATURE RESISTANCE (Dry) Continuous 200°F (93°C) Intermittent 250°F (121°C)

SHELF LIFE 24 months at recommended storage temperature.

FLASH POINT - SETA >100°F (38°C)

HEALTH & SAFETY Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

APPLICATION

COVERAGE RATES	Dry Mil (Microns)	Wet Mil (Microns)	Sq Ft/Gal (m ² /Gal)
Suggested	2.5 (65)	4.5 (115)	372 (34.6)
Minimum	2.0 (50)	3.5 (90)	465 (43.2)
Maximum	3.5 (90)	6.0 (150)	266 (24.7)

Allow for overspray and surface irregularities. Wet film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance.

MIXING Stir thoroughly, making sure no pigment remains on the bottom of the can.

THINNING Use No. 1 Thinner or mineral spirits. May thin up to 1% or 1.25 ounces per gallon.

TNEMEC PRIMERS | SERIES V10

APPLICATION EQUIPMENT

Air Spray

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss JGA	E	765 or 704	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	60-90 psi (4.2-6.2 bar)	10-20 psi (0.7-1.4 bar)

Low temperatures or longer hoses require higher pot pressure.

Airless Spray

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.015"-0.019" (381-483 microns)	3000-4000 psi (207-276 bar)	1/4" or 3/8" (6.4 or 9.5 mm)	60 mesh (250 microns)

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

Roller: Use high quality synthetic woven nap covers, 1/4" nap for smooth surfaces, 3/8" nap for rough surfaces.

Brush: Use high quality natural or synthetic bristle brushes.

SURFACE TEMPERATURE

Minimum 40°F (4°C) Maximum 120°F (49°C)

The surface should be dry and at least 5°F (3°C) above the dew point.

CLEANUP

Flush and clean all equipment immediately after use with the recommended thinner or mineral spirits.

†Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.