



H.B. TNEMEC-TUFCOAT SERIES 113

PRODUCT PROFILE

GENERIC DESCRIPTION	Waterborne Acrylic Epoxy
COMMON USAGE	High performance coating suitable for concrete, steel and other commonly used building materials. Features include high-build, low odor, non-yellowing white and fade resistant colors; easy cleanup and stain-, abrasion-, chemical- and moisture-resistance. Good exterior performance.
COLORS	Refer to Tnemec Color Guide.
FINISH	Satin
PERFORMANCE CRITERIA	Extensive test data available. Contact your Tnemec representative for specific test results.

COATING SYSTEM

PRIMERS	<p>Steel: Series 1, 10, 27, 37H, 66, N69, N69F, 90E-92, 90-97, H90-97, 115, 394, 530. Note: Series 10 and 37H are not recommended for frequently wet conditions. Allow Series 10 to cure one week and 37H to cure 30 days before topcoating. Note: When topcoating Series 1 or 394 with 113, maximum recoat time is three days.</p> <p>Galvanized Steel and Non-Ferrous Metal: Series 66, N69, N69F, 115</p> <p>Dense Concrete: Self-priming, Series 130, 218</p> <p>CMU: Series 54, 130, 218</p> <p>Drywall: Series 151</p> <p>Wood: Dry interior environments only, self-priming, Series 10-99W, 151-1051</p>
----------------	---

SURFACE PREPARATION

NEW CONCRETE & CMU	Allow to cure for 28 days. Level protrusions and mortar spatter. For optimum results, abrasive blast referencing SSPC-SP13/NACE 6, ICRI CSP 2-3 Surface Preparation of Concrete and Tnemec's Surface Preparation and Application Guide.
PAINTED SURFACES	Apply test patch to check adhesion. Remove loose paint and spot prime.
ALL SURFACES	Must be clean, dry and free of oil, grease, form release agents and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS	44.0 ± 2.0% (mixed) †
RECOMMENDED DFT	4.0 to 6.0 mils (100 to 150 microns) per coat. Note: Number of coats and thickness requirements will vary with substrate, application method and exposure. Contact your Tnemec representative.

CURING TIME	Temperature	To Touch	To Handle	To Recoat
	75°F (24°C)	30-45 minutes	2-3 hours	1-2 hours

Curing time varies with surface temperature, air movement, humidity and film thickness.

VOLATILE ORGANIC COMPOUNDS	<p>Unthinned 1.90 lbs/gallon (228 grams/litre)</p> <p>Thinned 5% (No. 59 Thinner) 2.03 lbs/gallon (243 grams/litre) †</p>
HAPS	<p>Unthinned: 2.59 lbs/gal solids</p> <p>Thinned 5% (No. 59 Thinner): 2.82 lbs/gal solids</p>
THEORETICAL COVERAGE	706 mil sq ft/gal (17.3 m ² /L at 25 microns). See APPLICATION for coverage rates. †
NUMBER OF COMPONENTS	Two: One Part A (4.5 gal) and One Part B (1/2 gal)
PACKAGING	<p>Five-Gallon Kit: Consists of approximately 4.5 gallons of Part A in a five gallon pail and a partially-filled, half-gallon jug of Part B. When mixed, yields five gallons (18.9L).</p> <p>One-Gallon Kit: Consists of a partially-filled one gallon can labeled Part A and a partially-filled pint can labeled Part B. When mixed, yields one gallon (3.79L).</p>
NET WEIGHT PER GALLON	11.11 ± 0.25 lbs (5.04 ± .11 kg) (mixed) †
STORAGE TEMPERATURE	Minimum 35°F (2°C) Maximum 110°F (43°C)
TEMPERATURE RESISTANCE	(Dry) Continuous 170°F (77°C) Intermittent 250°F (121°C)
SHELF LIFE	Part A: 24 months; Part B: 12 months at recommended storage temperature.
FLASH POINT - SETA	Part A: 190°F (88°C) Part B: 135°F (57°C)
HEALTH & SAFETY	<p>Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.</p> <p>Keep out of the reach of children.</p>

H.B. TNEME-TUFÇOAT | SERIES 113

APPLICATION

COVERAGE RATES

	Dry Mills (Microns)	Wet Mills (Microns)	Sq Ft/Gal (m ² /Gal)
Suggested	5.0 (125)	11.5 (290)	141 (13.1)
Minimum	4.0 (100)	9.0 (230)	176 (16.4)
Maximum	6.0 (150)	13.5 (345)	118 (10.9)

Allow for overspray and surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. †

MIXING

Always use the entire contents of A and B components. Stir contents of Part A, making sure no pigment remains on the bottom. Slowly add the contents of Part B to Part A while under agitation. Continue agitation until thoroughly mixed.

THINNING

Use clean water. For air, airless spray, brush or roller, thin up to 5% or 1/4 pint (190 mL) per gallon. To improve brush and roll properties, thin up to 5% or 1/4 pint (190 mL) per gallon by volume with No. 59 Thinner. **Note:** Thin only after Part B has been thoroughly mixed with Part A according to mixing instructions.

POT LIFE

48 hours at 50°F (10°C) 24 hours at 77°F (25°C) 16 hours at 100°F (38°C)

APPLICATION EQUIPMENT

Air Spray

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss JGA 510	.070"	765	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	50-70 psi (3.4-4.8 bar)	10-20 psi (0.7-1.4 bar)

Low temperatures or longer hoses require higher pot pressure.

Airless Spray

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.015"-0.019" (380-485 microns)	2400-3300 psi (165-228 bar)	1/4" or 3/8" (6.4 or 9.5 mm)	60 mesh (250 microns)

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

Roller: Use 1/4" (6.4 mm) synthetic woven nap rollers for smooth surfaces, use 1/2" to 3/4" (12.7 mm to 19 mm) synthetic woven nap rollers for rough surfaces.

Brush: Use a high quality nylon or synthetic bristle brush.

Touch-Up: To minimize variations in appearance, touch-up over existing Tneme-Tufcoat should be done by the same method as initial application.

SURFACE TEMPERATURE

Minimum 50°F (10°C) Maximum 120°F (49°C)

The surface should be dry and at least 5°F (3°C) above the dew point. Coating won't cure below minimum surface temperature.

CLEANUP

Clean all equipment immediately after use with clean water followed by a final washing with the recommended thinner or Ethanol.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.