



PRODUCT PROFILE

**GENERIC DESCRIPTION** Flexible Epoxy

**COMMON USAGE** Flexible epoxy underlayment for bridging small substrate cracks in concrete and to provide a protective waterproof membrane under aggregate reinforced flooring systems.

**COLORS** 33GR Gray. Please contact your Tnemec representative for special colors. **Note:** Epoxies chalk and yellow with age, extended exposure to UV and artificial lighting. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause amine blush, possibly affecting adhesion of subsequent topcoats.

COATING SYSTEM

**SURFACER/FILLER/PATCHER** Series 215, 218. **Note:** A repair kit of 201, with Part C fumed silica, is available for small patching/surfacing repairs. For more extensive repairs and additional information, contact your Tnemec representative or Tnemec Technical Services.

**PRIMERS** Series 201, 205.

**TOPCOATS** Series 210, 222, 223, 237, 238, 239, 247, 248, 270, 290, 291, 294, 295, 297. **Note:** When using 223, 237, 238 and 239 mortars, a tie coat of Series 201 is required.

SURFACE PREPARATION

**CONCRETE** Prepare surfaces by method suitable for exposure and service.  
 Allow new cast-in-place concrete to cure a minimum of 28 days at 75°F (24°C). Verify concrete dryness and prepare concrete surfaces in accordance with NACE No. 6/SSPC-SP13 Joint Surface Preparation Standards and ICRI Technical Guidelines. Moisture vapor transmission should not exceed three lbs per 1,000 sq ft in a 24 hour period (Reference ASTM F 1869 "Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride"). Relative humidity should not exceed 80% (Reference ASTM F 2170 "Standard Test Method for Determining Relative Humidity in Concrete using in situ Probes"). Abrasive blast, shot blast, water jet or mechanically abrade concrete surfaces to remove laitance, curing compounds, hardeners, sealers and other contaminants and to provide a minimum ICRI-CSP 3 or greater surface profile. Large cracks, voids and other surface imperfections should be filled with a recommended filler or surfacer.

**ALL SURFACES** Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

**VOLUME SOLIDS** 100% (mixed)

**RECOMMENDED DFT** 30.0 to 80.0 mils (750 to 2000 microns) per coat.

**CURING TIME**

Temperature	To Recoat	To Place in Service
75°F (24°C)	12-24 hours	24 hours

**Note:** If more than 24 hours have elapsed between coats, the coated surface must be mechanically abraded before topcoating.

**VOLATILE ORGANIC COMPOUNDS** **Unthinned:** 0.06 lbs/gallon (7 grams/litre)

**THEORETICAL COVERAGE** 1,604 mil sq ft/gal (39.4 m<sup>2</sup>/L at 25 microns). See APPLICATION for coverage rates.

**NUMBER OF COMPONENTS** Two: Part A and Part B (2 Parts A to 1 Part B by volume.)

**PACKAGING** KITS CONSIST OF:

	PART A (Partially filled)	PART B (Partially filled)	When Mixed Yield
Large Kit	2-5 gallon pails	1-5 gallon pail	15 gallons (56.8 L)
Small Kit	2-1 gallon cans	1-1 gallon can	3 gallons (11.4 L)

**NET WEIGHT PER GALLON** 9.45 ± 0.25 lbs (4.29 ± .11 kg) mixed

**STORAGE TEMPERATURE** Minimum 20°F (-7°C) Maximum 110°F (43°C)  
 Prior to application, the material temperature should be above 60°F (16°C). It is suggested the material be stored above this temperature at least 48 hours prior to use.

**SHELF LIFE** 12 months at recommended storage temperature.

**FLASH POINT - SETA** Part A: N/A Part B: N/A

**HEALTH & SAFETY** Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.  
**Keep out of the reach of children.**

# SUB-FLEX EP™ | SERIES 206

## APPLICATION

**COVERAGE RATES** Before commencing, obtain and thoroughly read the *StrataShield Installation and Application Guide* for floors.

	Dry Mills (Microns)	Wet Mills (Microns)	Sq Ft/Gal (m <sup>2</sup> /Gal)
Suggested	30.0-80.0 (750-2000)	30.0-80.0 (750-2000)	20-53 (1.9-4.9)

**Caution:** Before applying Series 206, voids and irregularities in the prepared and primed concrete substrate must first be filled using Series 215, 218 or thickened Series 201. Contact Tnemec Technical Service for detailed recommendations. Allow for surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance.

**MIXING** Use a variable speed drill with a PS Jiffy blade. Slowly mix 2 parts A component, and while under agitation, add 1 part B component and mix for a minimum of two minutes. Ensure that all Part B is blended with Part A by scraping the pail walls with a flexible spatula.

**Note:** A large volume of material will set up quickly if not applied or reduced in volume.

**Caution:** Do not reseal mixed material. An explosion hazard may be created.

**THINNING** DO NOT THIN.

**POT LIFE** 30-40 minutes at 75°F (24°C)

**APPLICATION EQUIPMENT** Notched squeegee or trowel and porcupine or loop roller (squeegee or trowel and backroll with porcupine or loop roller).

**SURFACE TEMPERATURE** Minimum of 55°F (13°C), optimum 65°F to 80°F (18°C to 27°C), maximum of 90°C (32°C). The substrate temperature should be at least 5°F (3°C) above the dew point. Coating will not cure below minimum surface temperature.

**MATERIAL TEMPERATURE** For optimum application, handling and performance, the material temperature during application should be between 70°F and 90°F (21°C and 32°C). Temperature will affect the workability. Cool temperatures increase viscosity and decrease workability. Warm temperatures will decrease viscosity and shorten pot life.

**CLEANUP** Clean all equipment immediately after use with MEK or xylene.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.