



# EVEN-FLOW SL<sup>®</sup> SERIES 210

## PRODUCT PROFILE

**GENERIC DESCRIPTION** Aggregate-Filled Modified Polyamine Epoxy

**COMMON USAGE** A high gloss, high build, self-leveling epoxy topping for concrete floors. It imparts an ultra smooth, aesthetically pleasing finish in a variety of colors, while providing protection against various acids and alkalis, abrasion and frequent cleaning.

**COLORS** Available in the 16 standard StrataShield colors. Special colors available, please contact your Tnemec representative. **Note:** Epoxies chalk and yellow with age, extended exposure to UV and artificial lighting. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause amine blush, possibly affecting adhesion of subsequent topcoats.

**FINISH** Gloss

## COATING SYSTEM

**SURFACER/FILLER/PATCHER** Series 63-1500, 206, 218, 219. **Note:** A repair kit of 201, with Part C fumed silica, is available for small patching/surfacing repairs. For more extensive repairs and additional information, contact your Tnemec representative or Tnemec Technical Services.

**PRIMERS** **Concrete Floors:** Series 201, 203, 205.

**TOPCOATS** Series 280, 281, 282, 290, 291, 294, 295, 296, 297

## SURFACE PREPARATION

Prepare surfaces by method suitable for exposure and service. Refer to the appropriate primer data sheet for specific recommendations.

**CONCRETE** Allow new concrete to cure 28 days. Verify dryness by testing for moisture with a "plastic film tape-down test." (Reference ASTM D 4263) Should moisture be detected, perform "Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride." (Reference ASTM F 1869) Moisture content not to exceed three pounds per 1,000 sq ft in a 24 hour period. Shot-blast or mechanically abrade to remove laitance, curing compounds, hardeners, sealers and other contaminants and to provide surface profile. Large voids, bugholes and other cavities should be filled with recommended filler or surfacer. (Reference SSPC-SP13, ICRI CSP3-5)

**ALL SURFACES** Must be clean, dry and free of oil, grease and other contaminants.

## TECHNICAL DATA

**VOLUME SOLIDS** 100% (mixed) †

**RECOMMENDED DFT** 30.0 to 100.0 mils (750 to 2500 microns) per coat. Additional coats may be required for appearance.

**CURING TIME**

Temperature	To Topcoat	To Place in Service
75°F (24°C)	10-24 hours	24 hours

**Note:** If more than 24 hours have elapsed between coats, the coated surface must be mechanically abraded before topcoating.

**VOLATILE ORGANIC COMPOUNDS** 0.06 lbs/gallon (7 grams/litre) †

**THEORETICAL COVERAGE** 1,604 mil sq ft/gal (39.4 m<sup>2</sup>/L at 25 microns). See APPLICATION for coverage rates. †

**NUMBER OF COMPONENTS** Three: Liquids — Part A and Part B (2 Parts A to 1 Part B by volume.)  
Aggregate Filler: Part C

**PACKAGING**

	PART A	PART B	PART C	Mixed Yield
Large Kit	2-5 gallon pails	1-5 gallon pail	5-5 gallon pails	21.6 gal. (81.8L)
Small Kit	2-1 gallon cans	1 gallon can	1-5 gallon pail	4.3 gal. (16.3L)

**NET WEIGHT PER GALLON** 13.70 ± 0.25 lbs (6.23 ± .11 kg) (mixed) †

**STORAGE TEMPERATURE** Minimum 40°F (4°C) Maximum 90°F (32°C)  
**Note:** Material should be stored at temperatures between 70°F and 90°F (21°C and 32°C) for at least 48 hours prior to use.

**TEMPERATURE RESISTANCE** (Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

**SHELF LIFE** 12 months at recommended storage temperature.

**FLASH POINT - SETA** N/A

**HEALTH & SAFETY** This product contains chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.  
**Keep out of the reach of children.**

# EVEN-FLOW SL® | SERIES 210

## APPLICATION

**COVERAGE RATES**

Before commencing, obtain and thoroughly read the StrataShield Installation and Application Guide for floors.

	Dry Mills (Microns)	Wet Mills (Microns)	Sq Ft/Gal (m <sup>2</sup> /Gal)
Horizontal	30.0-100.0 (750-2500)	30.0-100.0 (750-2500)	16-53 (1.5-4.9)

Allow for surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. †

**MIXING**

Use a variable speed drill with a PS Jiffy blade. Slowly mix 2 gallons of Part A component, and while under agitation, add 1 gallon of Part B component and mix for a minimum of two minutes. Ensure that all Part B is blended with Part A by scraping the pail walls with a flexible spatula. Slowly sift in entire contents of Part C aggregate-filler while under constant agitation using power mixer until thoroughly mixed. Immediately after mixing, material should be dispensed from containers onto floor surface to prevent settling of Part C. **Note:** The Part C component is packaged by weight and is designed to be added to 3 gallons of mixed 210 liquids. The ratio of Parts A, B & C should not be altered. Apply the mixed material within pot life limits after agitation.

**THINNING**

Do not thin.

**POT LIFE**

45 to 50 minutes at 70°F (21°C)    35 to 40 minutes at 80°F (27°C)    25 to 30 minutes at 90°F (32°)

**APPLICATION EQUIPMENT**

Notched squeegee, notched trowel or gauge rake, porcupine roller (squeegee, trowel or rake and porcupine roll).

**SURFACE TEMPERATURE**

Minimum of 55°F (13°C), optimum 65°F to 80°F (18°C to 27°C), maximum of 90°F (32°C). The substrate temperature should be at least 5°F (3°C) above the dew point.

**MATERIAL TEMPERATURE**

For optimum application, handling and performance, the material temperature during application should be between 70°F and 90°F (21°C and 32°C). Temperature will affect the workability. Cool temperatures increase viscosity and decrease workability. Warm temperatures will decrease viscosity and shorten pot life.

**CLEANUP**

Flush and clean all equipment immediately after use with xylene or MEK.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.