



DECO-CLEAR® CR SERIES 286

PRODUCT PROFILE

GENERIC DESCRIPTION Modified Novolac Polyamine Epoxy

COMMON USAGE A clear novolac finish for decorative flooring systems. It protects against harsh chemicals, impact and abrasion, providing a skid-resistant or smooth finish depending on the number of coats.

COLORS Clear. **Note:** Epoxies chalk and yellow with age, extended exposure to UV and artificial lighting. Caution should be taken when selecting white and light pastel colors. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause amine blush, possibly affecting adhesion of subsequent topcoats. **Caution: Novolacs will stain with extended exposure to certain acids.**

FINISH Gloss. The texture of the finished surface depends on the number of coats applied.

COATING SYSTEM

INTERMEDIATE TOPCOATS Series 222, 223, 224, 237, 238, 239
Series 286

SURFACE PREPARATION

ALL SURFACES Prepare surfaces by method suitable for exposure and service. Refer to the StrataShield Installation and Application Guide for floors or primer product data sheet for specific recommendations.
Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS 100% (mixed)

RECOMMENDED DFT As a finish coat: 8.0 to 12.0 mils (205 to 305 microns) per coat.

CURING TIME

Temperature	To Recoat	To Place in Service	Full Cure
75°F (24°C)	12-24 hours	24 hours	5 days

If more than 24 hours have elapsed between coats, the Deco-Clear CR coated surface must be mechanically abraded before topcoating. **Note:** 24 hour cure provides for traffic, secondary containment and certain mild chemical exposures. Up to five days cure is required for certain severe chemical exposures. Contact your Tnemec representative or Tnemec Technical Services.

VOLATILE ORGANIC COMPOUNDS 0.16 lbs/gallon (19 grams/litre)

THEORETICAL COVERAGE 1,604 mil sq ft/gal (39.4 m²/L at 25 microns). See APPLICATION for coverage rates.

NUMBER OF COMPONENTS Two: Part A and Part B (2 Parts A component to 1 Part B component by volume)

PACKAGING

	PART A	PART B	Yield (mixed)
Extra Large Kit	2-55 gallon drums	1-55 gallon drum	165 gallons
Large Kit	2-5 gallon pails	1-5 gallon pail	15 gallons
Small Kit	2-1 gallon cans	1-1 gallon can	3 gallons

NET WEIGHT PER GALLON 9.30 ± 0.25 lbs (4.22 ± .11 kg) (mixed)

STORAGE TEMPERATURE Minimum 40°F (4°C) Maximum 90°F (32°C)
Prior to application, the material temperature should be between 70°F and 90°F (21°C and 32°C).

TEMPERATURE RESISTANCE (Dry) Continuous 300°F (149°C) Intermittent 325°F (163°C)

SHELF LIFE 12 months at recommended storage temperature.

FLASH POINT - SETA N/A

HEALTH & SAFETY This product contains chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

DECO-CLEAR® CR | SERIES 286

APPLICATION

COVERAGE RATES

Before commencing, obtain and thoroughly read the StrataShield Installation and Application Guide for floors.

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m ² /Gal)
As a finish coat	8.0-12.0 (205-305)	8.0-12.0 (205-305)	160-240 (14.9-22.3)

Allow for surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance.

MIXING

Use a variable speed drill with a PS Jiffy blade. Slowly mix 2 parts A component, and while under agitation add 1 part B component and mix for a minimum of two minutes. Ensure that all Part B is blended with Part A by scraping the pail walls with a flexible spatula.

Note: A large volume of material will set up quickly if not applied or reduced in volume.

Caution: Do not reseal mixed material. An explosion hazard may be created.

THINNING

Normally not required.

POT LIFE

25 to 30 minutes at 75°F (24°C)

Increasing material temperatures will significantly reduce the pot life.

APPLICATION EQUIPMENT

Brush, roller, squeegee, trowel. Squeegee or trowel and backroll. Brush small areas only. For detailed instructions refer to the StrataShield Installation and Application Guide for floors.

SURFACE TEMPERATURE

Minimum of 55°F (13°C), optimum 65°F to 80°F (18°C to 27°C), maximum of 90°F (32°C). The substrate temperature should be at least 5°F (3°C) above the dew point.

MATERIAL TEMPERATURE

For optimum application, handling and performance, the material temperature during application should be between 70°F and 90°F (21°C and 32°C). Temperature will affect the workability. Cool temperatures increase viscosity and decrease workability. Warm temperatures will decrease viscosity and shorten pot life.

CLEANUP

Flush and clean all equipment immediately after use with xylene or MEK.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.