



PRODUCT PROFILE

GENERIC DESCRIPTION Ceramic-Modified Waterborne Aliphatic Polyurethane

COMMON USAGE Low odor, fast dry, low VOC, waterborne polyurethane coating for interior wall and floor applications. Provides enhanced abrasion resistance, stain resistance and color stability. This user friendly product has easy application and clean-up characteristics and may be applied over a properly prepared aged coating (test patch is recommended for compatibility). Contact your Tnemec representative for more details.

COLORS Refer to Tnemec and StrataShield Color Guide. **Note:** Certain colors may require multiple coats depending on method of application and finish coat color. When feasible, the preceding coat should be in the same color family.

FINISH Gloss

SPECIAL QUALIFICATIONS The resin used to manufacture this product was a recipient of the EPA's "Green Chemistry Challenge Award."

PERFORMANCE CRITERIA Contact your Tnemec representative for specific test results.

COATING SYSTEM

PRIMERS **Concrete:** Series 66, L69, L69F, N69, N69F, 84•, 104, 113•, 114•, 156•, 161, 201, 203, 205, 270, 273, 275, 280, 281, 287. •For use on vertical surfaces. **Note:** Two coats are required over 201 & 203 primers to ensure proper hide and coverage. **CMU:** 54-660, 130, 156, 218. Intermediate coat required (any of the above). **Drywall:** Series 151, 287
Steel: Series 25, 27, 66, L69, L69F, N68, N69, N69F, 84, 104, 161, 287
Galvanized Steel and Non-Ferrous Metal: Series 66, L69, L69F, N69, N69F, 161

TOPCOATS Series 296 (optional)

SURFACE PREPARATION

ALL SURFACES Prepare surfaces by method suitable for exposure and service. Refer to the appropriate primer data sheet for specific recommendations.
 Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS 57 ± 2.0% (mixed) †

RECOMMENDED DFT 2.0 to 3.0 mils (50 to 75 microns) per coat. **Note:** Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating aesthetics and performance. Number of coats and thickness requirements will vary with substrate, application method and exposure. Contact your Tnemec representative.

CURING TIME

Temperature	To Recoat	To Service	Full Cure
75°F (24°C)	8 hours	24 hours	72 hours

Curing time varies with surface temperature, air movement, humidity and film thickness.

VOLATILE ORGANIC COMPOUNDS

Unthinned: 0.74 lbs/gallon (89 grams/litre)
Thinned 15%: 0.74 lbs/gallon (89 grams/litre) †

THEORETICAL COVERAGE

914 mil sq ft/gal (22.4 m²/L at 25 microns). †

NUMBER OF COMPONENTS

Two: Part A and Part B

MIXING RATIO

By volume: 4 (Part A) to 1 (Part B)

PACKAGING

	PART A (Partially filled)	PART B (Partially filled)	When Mixed Yield
Large Kit	5 gallon pail	1 gallon can	5 gallons (18.9L)
Small Kit	1 gallon can	1 quart can	1 gallon (3.79L)

NET WEIGHT PER GALLON

11.98 ± 0.25 lbs (5.45 ± .11 kg) †

STORAGE TEMPERATURE

Minimum 40°F (4°C) Maximum 110°F (43°C)
 Protect from freezing.

TEMPERATURE RESISTANCE

(Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

SHELF LIFE

12 months at recommended storage temperature.

FLASH POINT - SETA

Part A: 113°F (45°C) Part B: >200°F (93°C)

HEALTH & SAFETY

Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

ENVIRO-GLAZE™ | SERIES 297

APPLICATION

COVERAGE RATES

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m ² /Gal)
Suggested	2.5 (65)	5.0 (125)	366 (34.0)
Minimum	2.0 (50)	4.0 (100)	457 (42.5)
Maximum	3.0 (75)	6.0 (150)	305 (28.3)

Allow for overspray and surface irregularities and waste. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. †

MIXING

Stir contents of the container marked Part A, making sure no pigment remains on the bottom. Add the contents of the container marked Part B to Part A **while under mechanical agitation**. Continue agitation until the two components are thoroughly mixed. Continue mechanical agitation and add potable water for thinning according to the thinning instructions. **Note:** Product must be thinned for proper application. Do not use mixed material beyond pot life limits. **Caution: Part B is moisture-sensitive and will react with atmospheric moisture. Keep unused material tightly closed at all times. Do not reseal mixed material. An explosion hazard may be created.** Unused material should be thinned with equal amounts of water by volume and disposed of properly.

THINNING

Use potable water for brush or roller. **Note:** Product must be thinned for proper application. For airless spray, thin up to 15% per gallon for wall applications or up to 20% per gallon for floor applications. **Note:** Thin with mechanical agitation only after Part B has been thoroughly mixed with Part A according to mixing instructions. Exceeding pot life may affect gloss.

POT LIFE

2 hours at 77°F (25°C). **Note:** Exceeding pot life may result in lower gloss finish.

APPLICATION EQUIPMENT

Brush, roller and airless spray.

Roller: Use high quality 1/4" nap, shed resistant, woven fabric roller cover.

Brush: Use high quality synthetic or nylon bristle brush.

Horizontal: Apply by roller. Brush small areas only.

Vertical: Roll or spray and backroll. Brush small areas only.

Material can be transferred to the surface through application equipment including a Graco "King" 45:1 or 56:1 airless spray pump or other airless spray equipment of equal or grater configuration an capability, immediately followed by backrolling. **Note:** Spraying should only be considered as means to transfer the material to the surface. Uniform film thickness may be difficult to achieve without backrolling. Caution should be exercised to not exceed recommended maximum 6 mils WFT.

SURFACE TEMPERATURE

Minimum 40°F (4°C) Maximum 120°F (49°C)

The surface should be dry and at least 5°F (3°C) above the dew point.

CLEANUP

Flush and clean all equipment immediately after use with water and flush with xylene.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.