



CHEM-PRIME H.S. SERIES 37H

PRODUCT PROFILE

GENERIC DESCRIPTION Phenolic Alkyd

COMMON USAGE Lead- and chromate-free, fast-drying, corrosion-resistant primer that accepts a variety of high-performance topcoats. Ideally suited for steel fabricators, OEM's and field applications where "dry-fall" characteristics are desired. **Note:** Not recommended for immersion.

COLORS 77 Red, 78 Gray. **Note:** Minimum order quantities apply for 78 Gray.

PERFORMANCE CRITERIA Extensive test data available. Contact your Tnemec representative for specific test results.

COATING SYSTEM

TOPCOATS Series 2H, 2HS, 6, 27, 30, 66, L69, L69F, N69, N69F, V69, V69F, 73, 113, 114, 161, 175, 180, 181, 1028, 1029, 1074, 1074U, 1075, 1075U. Allow Series 37H to cure for three days before topcoating with 1028 or 1029.
Note: Some systems are not recommended for frequently sweating or continually wet conditions. Reference the applicable topcoat data sheet for additional information. Also, an additional coat of 37H is suggested before applying Series 6, 180, 181, 1028 or 1029. Contact Tnemec Technical Services for details.

SURFACE PREPARATION

STEEL **Enclosed or Protected:** SSPC-SP3 Power Tool Cleaning
Weather-Exposed: SSPC-SP6/NACE 3 Commercial Blast Cleaning

CAST/DUCTILE IRON Contact your Tnemec representative or Tnemec Technical Services.

ALL SURFACES Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS 58.0 ± 2.0% †

RECOMMENDED DFT 2.0 to 3.5 mils (50 to 90 microns) per coat.

CURING TIME **Temperature:** 75°F (24°C)
To Handle: 2 hours
To Recoat With Series:

2H, 2HS, 180, 181	27•, 66•, 161•	1028, 1029	30	L69, L69F, N69, N69F, V69, V69F, 73, 113, 114, 175, 1074, 1074U, 1075, 1075U
12 hours	48 hours	3 days	7 days	30 days

Curing time varies with surface temperature, air movement, humidity and film thickness.
Note: Allow 37H to cure 14 days if 27, 66 or 161 is to be used as an intermediate coat and topcoated with 73, 175, 1074, 1074U, 1075 or 1075U. Then allow 27, 66 or 161 to cure an additional 24 hours before topcoating.
Water Tank Exteriors: Five days or more curing required before filling.

VOLATILE ORGANIC COMPOUNDS **Unthinned:** 2.91 lbs/gallon (348 grams/litre)
Thinned 4%: 3.07 lbs/gallon (368 grams/litre)
Thinned 9%: 3.27 lbs/gallon (391 grams/litre) †

HAPS **Unthinned:** 1.37 lbs/gal solids
Thinned 4%: 1.89 lbs/gal solids
Thinned 9%: 2.51 lbs/gal solids

THEORETICAL COVERAGE 930 mil sq ft/gal (22.8 m²/L at 25 microns). See APPLICATION for coverage rates. †

NUMBER OF COMPONENTS One

PACKAGING 55 gallon (208.2L) drums, 5 gallon (18.9L) pails and 1 gallon (3.79L) cans.

NET WEIGHT PER GALLON
 77 12.83 ± 0.25 lbs (5.92 ± .11 kg)
 78 12.11 ± 0.25 lbs (5.61 ± .11 kg) †

STORAGE TEMPERATURE Minimum 20°F (-7°C) Maximum 110°F (43°C)

TEMPERATURE RESISTANCE (Dry) Continuous 200°F (93°C) Intermittent 250°F (121°C)

SHELF LIFE 24 months at recommended storage temperature.

FLASH POINT - SETA 65°F (18°C)

HEALTH & SAFETY Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

CHEM-PRIME H.S. | SERIES 37H

APPLICATION

COVERAGE RATES

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m ² /Gal)
Suggested	2.5 (65)	4.5 (115)	372 (34.6)
Minimum	2.0 (50)	3.5 (90)	465 (43.2)
Maximum	3.5 (90)	6.0 (150)	266 (24.7)

Allow for overspray and surface irregularities. Wet film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. †

MIXING

THINNING

APPLICATION EQUIPMENT

Stir thoroughly, making sure no pigment remains on the bottom of the can.

Use No. 2 Thinner. For air spray, thin up to 9% per gallon. For airless spray, brush or roller, thin up to 4% per gallon.

Air Spray

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss JGA	E	765 or 704	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	75-90 psi (5.2-6.2 bar)	10-20 psi (0.7-1.4 bar)

Low temperatures or longer hoses require higher pot pressure.

Airless Spray

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.015"-0.019" (380-485 microns)	2700-3000 psi (186-207 bar)	1/4" or 3/8" (6.4 or 9.5 mm)	60 mesh (250 microns)

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

Roller: Use high quality synthetic woven nap covers, 1/4" nap for smooth surfaces, 3/8" nap for rough surfaces.

Brush: Recommended for small areas only. Use high quality nylon or synthetic bristle brushes.

SURFACE TEMPERATURE

Minimum 40°F (4°C) Maximum 120°F (49°C)

The surface should be dry and at least 5°F (3°C) above the dew point.

CLEANUP

Flush and clean all equipment immediately after use with the recommended thinner or xylol.

CAUTION

Dry overspray can be wiped or washed from most surfaces. Satisfactory dry-fall performance depends upon height of work, weather conditions, equipment adjustment and proper thinning. Test for each application as follows: Spray from 15 to 25 feet towards paint container. The material then should readily wipe off. **Note:** Heat can fuse-dry overspray to surfaces. Always clean dry overspray from hot surfaces before fusing occurs. Be aware that exterior surface temperatures can be higher than air temperature.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.