



PRODUCT PROFILE

GENERIC DESCRIPTION Polyamide Epoxy-Coal Tar

COMMON USAGE High-build corrosion resistant coating providing one coat protection for concrete and steel in a variety of chemical, immersion and underground conditions. Also, when a two-coat application is desired, a low film build option is possible.

COLORS Black

FINISH Semi-gloss

SPECIAL QUALIFICATIONS Conforms to the performance requirements of AWWA C 210 (not for potable water contact).

PERFORMANCE CRITERIA Extensive test data available. Contact your Tnemec representative for specific test results.

COATING SYSTEM

PRIMERS **Steel:** Self-priming or Series 1, 66, N69, N69F, 90-97, H90-97, 161
Galvanized Steel: Series 66, N69, N69F, 161
Concrete: Self-priming, 63-1500, 218

SURFACE PREPARATION

STEEL **Immersion Service:** SSPC-SP10 Near-White Blast Cleaning
Non-Immersion Service: SSPC-SP6 Commercial Blast Cleaning

GALVANIZED STEEL Surface preparation recommendations will vary depending on substrate and exposure conditions. Contact your Tnemec representative or Tnemec Technical Services.

CAST/DUCTILE IRON Contact your Tnemec representative or Tnemec Technical Services.

CONCRETE Allow new concrete to cure for 28 days. Abrasive blast all surfaces referencing SSPC-SP13/NACE 6, ICRI CSP 2-4 Surface Preparation of Concrete and Tnemec's Surface Preparation and Application Guide.

PRIMED SURFACES **Immersion Service:** Scarify the surface with fine abrasive before topcoating if the Series 66, N69 or 161 prime coat has been exposed to sunlight for 60 days or longer.

ALL SURFACES Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS 75.0 ± 2.0% (mixed)

RECOMMENDED DFT 16.0 to 20.0 mils (405 to 510 microns)
 8.0 to 10.0 mils (200 to 250 microns) for the two-coat option

CURING TIME

| Temperature | To Touch | To Recoat (Min./Max) | Immersion |
|-------------|----------|----------------------|------------|
| 95°F (35°C) | 2 hours | 3-14 hours | 5 days |
| 85°F (29°C) | 3 hours | 4-18 hours | 6 days |
| 75°F (24°C) | 4 hours | 6-28 hours | 7 days |
| 65°F (18°C) | 6 hours | 10-50 hours | 10 days |
| 55°F (13°C) | 9 hours | 16 hrs-3 days | 14-16 days |
| 45°F (7°C) | 18 hours | 32 hrs-4 days | 22-24 days |
| 35°F (2°C) | 26 hours | 44 hrs-6 days | 28-32 days |

Curing time varies with surface temperature, air movement, humidity and film thickness. Use the above times as guidelines only. Scarify the surface with fine abrasive before recoating if the maximum recoat time has been exceeded.

VOLITILE ORGANIC COMPOUNDS

Unthinned: 1.91 lbs/gallon (229 grams/litre)
Thinned 20% (No. 2 Thinner): 2.80 lbs/gallon (335 grams/litre)
Thinned 20% (No. 65 Thinner): 1.91 lbs/gallon (229 grams/litre)

THEORETICAL COVERAGE

1,203 mil sq ft/gal (29.5 m²/L at 25 microns). See APPLICATION for coverage rates.

NUMBER OF COMPONENTS

Two: Part A and Part B

MIXING RATIO

By volume: One (Part A) to one (Part B)

PACKAGING

5 gallon (18.9L) pails and 1 gallon (3.79L) cans — Order in multiples of 2.

NET WEIGHT PER GALLON

11.74 ± 0.25 lbs (5.32 ± .11 kg) (mixed)

STORAGE TEMPERATURE

Minimum 20°F (-7°C) Maximum 110°F (43°C)

TEMPERATURE RESISTANCE

(Dry) Continuous 200°F (93°C) Intermittent 250°F (121°C)

SHELF LIFE

12 months at recommended storage temperature.

FLASH POINT - SETA

Parts A & B: 81°F (27°C)

HEALTH & SAFETY

Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

HI-BUILD TNEME-TAR® | SERIES 46H-413

APPLICATION

COVERAGE RATES

Conventional Build

| | Dry Mils (Microns) | Wet Mils (Microns) | Sq Ft/Gal (m ² /Gal) |
|-----------|--------------------|--------------------|---------------------------------|
| Suggested | 18.0 (455) | 24.0 (610) | 69 (6.4) |
| Minimum | 16 (405) | 21.5 (545) | 75 (7.0) |
| Maximum | 20.0 (510) | 27.0 (685) | 59 (5.5) |

Two-Coat System (DFT each coat)

| | Dry Mils (Microns) | Wet Mils (Microns) | Sq Ft/Gal (m ² /Gal) |
|-----------|--------------------|--------------------|---------------------------------|
| Suggested | 9.0 (225) | 12.0 (300) | 134 (12.5) |
| Minimum | 8.0 (200) | 11.0 (275) | 150 (14.0) |
| Maximum | 10.0 (250) | 13.0 (325) | 120 (11.2) |

Allow for overspray and surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance.

MIXING

Power mix contents of each container, making sure no pigment remains on the bottom. Pour a measured amount of Part B into a clean container large enough to hold both components. Add an equal volume of Part A to Part B while under agitation. Continue agitation until the two components are thoroughly mixed. Do not use mixed material beyond pot life limits. **Note:** Both components should be above 50°F (10°C) prior to mixing. For application to surfaces between 35°F to 50°F (2°C to 10°C), allow mixed material to stand thirty (30) minutes and restir before using. For optimum application properties, the material temperature should be above 60°F (16°C).

THINNING

Use No. 2 Thinner. For air spray, thin up to 20% or 1 1/2 pints (760 mL) per gallon; for airless spray, thin up to 5% or 1/4 pint (190 mL) per gallon. A maximum of 20% of No. 65 Thinner may be used to comply with VOC regulations.

POT LIFE

16 hours at 35°F (2°C) 6 hours at 55°F (13°C) 2 hours at 75°F (24°C) 3/4 hour at 95°F (35°C)

APPLICATION EQUIPMENT

Air Spray

| Gun | Fluid Tip | Air Cap | Air Hose ID | Mat'l Hose ID | Atomizing Pressure | Pot Pressure |
|---------------|------------|------------|----------------------------------|-------------------|-----------------------------|----------------------------|
| DeVilbiss JGA | E .070" | 704 or 765 | 5/16" or 3/8" (7.9 or 9.5 mm) | 1/2" (12.7 mm) | 75-100 psi (5.2-6.9 bar) | 20-40 psi (1.4-2.8 bar) |

Low temperatures or longer hoses require higher pot pressure.

Airless Spray

| Tip Orifice | Atomizing Pressure | Mat'l Hose ID | Manifold Filter |
|------------------------------------|--------------------------------|----------------------------------|--------------------------|
| 0.017"-0.021" (430-530 microns) | 3400-4000 psi (234-276 bar) | 3/8" or 1/2" (9.5 or 12.7 mm) | 60 mesh (250 microns) |

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

Note: Application over inorganic zinc-rich primers: Apply a wet mist coat and allow tiny bubbles to form. When bubbles disappear in 1 to 2 minutes, apply a full wet coat at specified mil thickness.

Brush: Brushing is recommended on small areas only. Ladle material on and then use flat side of brush to spread. Do not brush out to thin film as with conventional coatings.

SURFACE TEMPERATURE

Minimum 35°F (2°C) Maximum 120°F (49°C)
The surface should be dry and at least 5°F (3°C) above the dew point. Coating won't cure below minimum surface temperature.

CLEANUP

Flush and clean all equipment immediately after use with the recommended thinner or xylol.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.