



PRODUCT PROFILE

<b>GENERIC DESCRIPTION</b>	Moisture-Cured Aromatic Urethane
<b>COMMON USAGE</b>	Aluminum pigmented primer or finish for marginally cleaned steel. Provides excellent abrasion-, moisture-, chemical- and corrosion-resistance. Suitable for use as a topcoat where an aluminum finish is desired. Topcoating provides enhancement of systems and more latitude with color. Compatible with aged coatings, but verify with test patch.
<b>COLORS</b>	Aluminum
<b>FINISH</b>	Matte
<b>PERFORMANCE CRITERIA</b>	Extensive test data available. Contact your Tnemec representative for specific test results.

COATING SYSTEM

<b>TOPCOATS</b>	Series 2H, 23, 27, 66, N69, 73, 113, 114, 161, 175, 530, 700, 1070, 1071, 1072, 1074, 1075, 1077 <b>Note:</b> Series 530 exterior (sunlight) exposed for 24 hours or longer requires scarification or an intermediate coat of Series 27, 66 or N69 prior to topcoating with itself (530), 73, 175, 700, 1070, 1071, 1072, 1074, 1075 or 1077. Also if exterior exposed for 7 days or longer, 530 requires scarification or an intermediate coat of 27, 66 or N69 prior to topcoating with 113 or 114. The intermediate coat color should be noticeably different but in the same family as the specified topcoat color.
-----------------	--

SURFACE PREPARATION

<b>STEEL</b>	<b>Moderate Exposure:</b> SSPC-SP3 Power Tool Cleaning or SSPC-SP2 Hand Tool Cleaning <b>Severe Exposure:</b> SSPC-SP6 Commercial Blast Cleaning
<b>ALL SURFACES</b>	Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

<b>VOLUME SOLIDS</b>	51.0 ± 2.0%
<b>RECOMMENDED DFT</b>	2.0 to 3.0 mils (50 to 75 microns) per coat. <b>Note:</b> Number of coats required will vary depending on exposure conditions and other variables. Contact your Tnemec representative.

CURING TIME

Temperature	To Touch	To Handle	To Recoat
75°F (24°C) (50% Relative Humidity)	2 to 2-1/2 hours	2-1/2 to 3 hours	5 hours

Curing time varies with surface temperature, air movement, humidity and film thickness.  
**Note:** For faster curing and low-temperature applications, add No. 44-710 Urethane Accelerator; see separate product data sheet.

VOLATILE ORGANIC COMPOUNDS

**Unthinned:** 3.49 lbs/gallon (418 grams/litre)

THEORETICAL COVERAGE

818 mil sq ft/gal (20.1 m<sup>2</sup>/L at 25 microns). See APPLICATION for coverage rates.

NUMBER OF COMPONENTS

One

PACKAGING

5 gallon (18.9L) pails and 1 gallon (3.79L) cans.

NET WEIGHT PER GALLON

9.16 ± 0.25 lbs (4.15 ± .11 kg)

STORAGE TEMPERATURE

Minimum 20°F (-7°C) Maximum 110°F (43°C)

TEMPERATURE RESISTANCE

(Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

SHELF LIFE

12 months at recommended storage temperature.

FLASH POINT - SETA

100°F (38°C)

HEALTH & SAFETY

Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.  
**Keep out of the reach of children.**

APPLICATION

COVERAGE RATES

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m <sup>2</sup> /Gal)
Suggested	2.5 (65)	5.0 (125)	327 (30.4)
Minimum	2.0 (50)	4.0 (100)	409 (38.0)
Maximum	3.0 (75)	6.0 (150)	273 (25.3)

Allow for overspray and surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance.

MIXING

Stir thoroughly, making sure no pigment remains on the bottom of the can. This product reacts with moisture. Viscosity will remain constant if material is kept dry. Keep unused material tightly closed at all times. Avoid vigorous agitation that will incorporate excessive amounts of humid air into the product.

THINNING

DO NOT THIN. Viscosity will remain constant provided the container is covered. See mixing instructions for further information.

# OMNITHANE® | SERIES 530

**APPLICATION EQUIPMENT**

**Air Spray**

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss MBC or JGA	E	78	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	60-80 psi (4.2-5.5 bar)	10-20 psi (0.7-1.4 bar)

Low temperatures or longer hoses require higher pot pressure.

**Airless Spray**

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.013"-0.017" (330-430 microns)	1800-3000 psi (124-207 bar)	1/4" or 3/8" (6.4 or 9.5 mm)	60 mesh (250 microns)

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

**Warning:** Avoid contamination with alcohol type thinners.

**Roller:** Use carpet-type roller covers.

**Brush:** Use high quality natural or synthetic bristle brushes.

**SURFACE TEMPERATURE**

Minimum 35°F (2°C) Maximum 120°F (49°C)

The surface should be dry and at least 5°F (3°C) above the dew point. **Caution: Application at film thicknesses exceeding 3.0 dry mils (75 microns) per coat or at relative humidities above 70% R.H. may cause bubbles to form in the cured film.**

**CLEANUP**

Flush and clean all equipment immediately after use with xylol.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.