



# POTA-POX® PLUS SERIES L140F

## PRODUCT PROFILE

- GENERIC DESCRIPTION** Polyamidoamine Epoxy
- COMMON USAGE** Versatile epoxy coating (factory accelerated version of L140) for protection and finishing of steel. It has excellent resistance to abrasion and is suitable for immersion service. This product can be used for lining storage tanks that contain demineralized, deionized or distilled water.
- COLORS** F1255 Beige, 1211 Red, F15BL Tank White. **Note:** Epoxies chalk with extended exposure to sunlight. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause yellowing to occur.
- SPECIAL QUALIFICATIONS** Certified by **NSF International** in accordance with **ANSI/NSF Std. 61**. Series L140F is qualified for use on tanks of 50,000 gallons (189,270.6L) capacity or greater and fittings one (1) inch (2.5 cm) in diameter or greater. Reference the "Search Listings" section of the NSF website at [www.nsf.org](http://www.nsf.org) for details on the maximum allowable DFT.
- PERFORMANCE CRITERIA** Extensive test data available. Contact your Tnemec representative for specific test results.

## COATING SYSTEM

- PRIMERS** Self-priming, 1, 91-H<sub>2</sub>O, 94-H<sub>2</sub>O, N140, N140F, L140, V140, V140F, 141
- TOPCOATS** **Interior:** Series 22, FC22, L140, L140F, N140, N140F, V140, V140F, 141  
**Exterior:** Series 27, 66, L69, L69F, N69, N69F, V69, V69F, 72, 73, L140, L140F, N140, N140F, V140, V140F, 156, 157, 161, 175, 180, 181, 446, 740, 750, 1028, 1029, 1074, 1074U, 1075, 1075U, 1080, 1081. Refer to COLORS on applicable topcoat data sheets for additional information. **Note:** The following recoat times apply for Series L140F: Immersion Service—Surface must be scarified after 30 days. Atmospheric Service—After 30 days, scarification or an epoxy tie-coat is required. When topcoating with Series 740 or 750, recoat time for L140F is 14 days. Contact your Tnemec representative for specific recommendations.

## SURFACE PREPARATION

- PRIMED STEEL** **Immersion Service:** Scarify the Series L140F prime coat surface by abrasive-blasting with fine abrasive before topcoating if it has been exterior exposed for 30 days or longer and L140F is the specified topcoat.
- STEEL** **Immersion Service:** SSPC-SP10/NACE 2 Near-White Blast Cleaning with a minimum angular anchor profile of 1.5 mils.  
**Non-Immersion Service:** SSPC-SP6/NACE 3 Commercial Blast Cleaning with a minimum angular anchor profile of 1.5 mils.
- CAST/DUCTILE IRON** Contact Tnemec Technical Services.
- CONCRETE** Allow new concrete to cure 28 days. For optimum results and/or immersion service, abrasive blast referencing SSPC-SP13/NACE 6, ICRI-CSP 2-4 Surface Preparation of Concrete and Tnemec's Surface Preparation and Application Guide. Fill all holes, pits, voids and cracks with 215 or 218.
- ALL SURFACES** Must be clean, dry and free of oil, grease and other contaminants.

## TECHNICAL DATA

- VOLUME SOLIDS** 66.0 ± 2.0% (mixed) †
- RECOMMENDED DFT** 2.0 to 10.0 mils (50 to 255 microns) per coat. **Note:** Number of coats and thickness requirements will vary with substrate, application method and exposure. Contact your Tnemec representative.

### CURING TIME AT 5 MILS DFT

Temperature	To Handle	To Recoat	Immersion
75°F (24°C)	4 hours	5 hours	7 days
65°F (18°C)	7-8 hours	9-11 hours	8 days
55°F (13°C)	12-14 hours	16-20 hours	9-10 days
45°F (7°C)	18-22 hours	28-32 hours	12-13 days
35°F (2°C)	28-32 hours	46-50 hours	16-18 days

Curing time varies with surface temperature, air movement, humidity and film thickness.  
**Ventilation:** When used in enclosed areas, provide adequate ventilation during application and cure.

### VOLATILE ORGANIC COMPOUNDS

**Unthinned:** 0.79 lbs/gallon (95 grams/litre)  
**Thinned 5% (No. 49 Thinner):** 0.79 lbs/gallon (95 grams/litre) †

### HAPS

**Unthinned:** 0 lbs/gal solids  
**Thinned 5% (No. 49 Thinner):** 0 lbs/gal solids

### THEORETICAL COVERAGE

1,059 mil sq ft/gal (26.0 m<sup>2</sup>/L at 25 microns). See APPLICATION for coverage rates. †

### NUMBER OF COMPONENTS

Two: Part A (amine) and Part B (epoxy) — One (Part A) to one (Part B) by volume.

### PACKAGING

5 gallon (18.9L) pails and 1 gallon (3.79L) cans — Order in multiples of 2.

### NET WEIGHT PER GALLON

14.62 ± 0.25 lbs (6.63 ± .11 kg) (mixed) †

### STORAGE TEMPERATURE

Minimum 20°F (-7°C) Maximum 110°F (43°C)  
For optimum application properties, material temperature should be above 60°F (16°C) prior to application.

### TEMPERATURE RESISTANCE

(Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

### SHelf LIFE

12 months at recommended storage temperature.

### FLASH POINT - SETA

Part A: 98°F (37°C) Part B: 95°F (35°C)

# POTA-POX® PLUS | SERIES L140F

**HEALTH & SAFETY**

Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.  
**Keep out of the reach of children.**

**APPLICATION**

**COVERAGE RATES**

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m <sup>2</sup> /Gal)
Suggested	6.0 (150)	9.0 (230)	176 (16.4)
Minimum	2.0 (50)	3.0 (75)	529 (49.2)
Maximum	10.0 (255)	15.0 (375)	106 (9.8)

**Note:** Roller or brush application requires two or more coats to obtain recommended film thickness. Allow for overspray and surface irregularities. Wet film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. Reference the "Search Listings" section of the NSF website at [www.nsf.org](http://www.nsf.org) for details on the maximum allowable DFT. †

**MIXING**

1. Start with equal amounts of both Parts A & B.
2. Using a power mixer, separately stir Parts A & B.
3. Add Part A to Part B under agitation, stir until thoroughly mixed.
4. Both components should be above 50°F (10°C) prior to mixing. For application to surfaces between 35°F to 50°F (2°C to 10°C), allow mixed material to stand 30 minutes and restir before using. For optimum application properties, blended components should be above 60°F (16°C).

**THINNING**

Use No. 49 Thinner. For air spray, thin up to 5% or 1/4 pint (190 mL) per gallon. No thinning necessary for airless spray. For roller or brush application, thin up to 5% or 1/4 pint (190 mL) per gallon.

**POT LIFE**

2 hours at 75°F (24°C)

**SPRAY LIFE**

30 minutes at 75°F (24°C)

**Note:** Spray application after listed times will adversely affect ability to achieve recommended dry film thickness.

**APPLICATION EQUIPMENT**

**Air Spray**

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss JGA	E	704	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	70-90 psi (4.8-6.2 bar)	10-20 psi (0.7-1.4 bar)

Low temperatures or longer hoses require higher pot pressure.

**Airless Spray**

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.015"-0.019" (380-485 microns)	3500-5100 psi (241-351 bar)	1/4" or 3/8" (6.4 or 9.5 mm)	60 mesh (250 microns)

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

**Roller:** Use a 3/8" or 1/2" (9.5 mm or 12.7 mm) synthetic woven nap roller cover. Use longer nap to obtain penetration on rough or porous surfaces.

**Brush:** Recommended for small areas only. Use high quality natural or synthetic bristle brushes.

**SURFACE TEMPERATURE**

Minimum 35°F (2°C) Maximum 135°F (57°C)

The surface should be dry and at least 5°F (3°C) above the dew point. Coating will not cure below minimum surface temperature.

**CLEANUP**

Flush and clean all equipment immediately after use with the recommended thinner or MEK.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.