



## GLASS BEADS 211-212 &amp; 213

## PRODUCT PROFILE

<b>GENERIC DESCRIPTION</b>	Glass Bead Additive
<b>COMMON USAGE</b>	Provides enhanced slip-resistance in select StrataShield topcoats for added safety.
<b>SIZE</b>	212 (50-80 mesh coarse bead) and 213 (70-140 mesh fine bead).

## COATING SYSTEM

<b>TOPCOATS</b>	Series 205, 247, 248, 287, 290, 291, 294, 295, 297
-----------------	--

## TECHNICAL DATA

<b>PACKAGING</b>	Small Kit: 1 Quart (32 volume ounces)    Large Kit: 1 Gallon (128 volume ounces)
<b>NET WEIGHT PER GALLON</b>	12.6 ± 0.25 lbs.
<b>HEALTH &amp; SAFETY</b>	Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product. <b>Keep out of the reach of children.</b>

## APPLICATION

<b>MIXING</b>	While under agitation, slowly add the glass beads in an amount between 2 to 4 ounces by volume per mixed gallon. A measuring cup is provided for this purpose to ensure proper distribution of the glass bead and a uniform appearance. It is recommended that the material be dipped and rolled out of either a pan or tray. If applied out of a bucket, the material should be periodically agitated to ensure the beads continue to stay in suspension. Ribboning the liquids and then spreading the material with a flat squeegee is not recommended since the beads may lay out unevenly, resulting in a patchy appearance.
---------------	--

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.

Tnemec Company Incorporated 6800 Corporate Drive Kansas City, Missouri 64120-1372 1-800-TNEMEC1 Fax: 1-816-483-3969 www.tnemec.com

