



NOTE: USE SERIES 215 OR SERIES 201, 237SC, OR 239SC 100% SOLIDS EPOXY MIXED WITH FUMED SILICA OR SILICA FLOUR FOR FILLER MATERIAL. ROUTE OUT CRACK PRIOR TO PATCHING IF CRACK IS LARGER THAN 1/16" (1.58mm).

TNEMEC
STANDARD SECONDARY CONTAINMENT LINING DETAILS

TREATMENT FOR NON-MOVING CRACKS

SCS-03

REV.0