



PRODUCT PROFILE

- GENERIC DESCRIPTION** HDP Acrylic Polymer
- COMMON USAGE** Water-based, low VOC, High Dispersion Pure acrylic polymer coating providing excellent long term protection in both interior/exterior exposures. May be applied by spray, brush or roller over a variety of solvent and waterborne steel primers. May also be used over many aged coatings. It is mildew resistant and exhibits very good gloss and color stability. Application methods include "dry-fall" under certain conditions (See Application). **Note:** Series 1029's "dry-fall" characteristics help reduce the potential for overspray problems on buildings and surrounding property.
- COLORS** Refer to Tnemec Color Guide. **Note:** Certain colors may require multiple coats depending on method of application and finish coat color. When feasible, the preceding coat should be in the same color family (blue, gray, etc.), but noticeably different.
- FINISH** Low semi-gloss - **Note:** Final gloss level of topcoat can vary depending on number of coats applied. One coat will generally result in a lower sheen than two coats of the material.

COATING SYSTEM

- PRIMERS**
 - Wood:** Series 10-99W, V10-99W or 151-1051
 - Steel:** Series 1, 10, 22, 30, 37H, 66, L69, L69F, N69, N69F, V69, V69F, 90-97, 90G-1K97, 91-H₂O, 94-H₂O, 113, 115, 135, L140, L140F, N140, N140F, V140, V140F, 141, 161, 287, 394. **Note:** Allow Series 10, V10 and 37H to cure three days before topcoating. Additionally, Series 1, 90-97, 90G-1K97, 91-H₂O, 94-H₂O and 394 must be exterior exposed for three days prior to topcoating. **Note:** This product exhibits direct-to-metal capabilities for dry interior environments. Contact Tnemec Technical Service for more information.
 - Aluminum & Galvanized:** Series 66, L69, L69F, N69, N69F, V69, V69F, 115, 135
 - Concrete:** Self-priming or Series 6, 54, 66, L69, L69F, N69, N69F, V69, V69F, 130, 151, 156, 180, 287, 1254
 - CMU:** Series 54, 130, 1254
 - Drywall:** Series 51, 151-1051, 287
- TOPCOATS** Series 1028, 1080, 1081

SURFACE PREPARATION

- STEEL**
 - Weather Exposed:** SSPC-SP6 Commercial Blast Cleaning.
 - Enclosed, Protected & Mild Environments:** SSPC-SP2 Hand Tool or SSPC-SP3 Power Tool Cleaning.
- GALVANIZED STEEL & ALUMINUM** Surface preparation recommendations will vary depending on substrate and exposure conditions. Consult the latest version of Tnemec Technical Bulletin 10-78 or contact your Tnemec representative or Tnemec Technical Services.
- PAINTED SURFACES** Remove chalk and old paint not tightly bonded to the surface. Clean all visible rust using SSPC-SP3 Power Tool Cleaning (interior dry) or to bare metal using SSPC-SP11 Power Tool Cleaning to Bare Metal (weather exposed).
- PRIMED SURFACES** Must be clean, dry and free of dust, dirt, oil, grease and other contaminants. Existing water soluble stains in the substrate or upon the surface must be removed or sealed. Allow concrete to cure 28 days.

TECHNICAL DATA

- VOLUME SOLIDS** 40.0 ± 2.0% †
- RECOMMENDED DFT** 2.0 to 3.0 mils (50 to 75 microns) per coat.
- CURING TIME**

| Temperature | To Touch | To Handle | To Recoat | To Resist Moisture |
|-------------|------------|-----------|-----------|--------------------|
| 75°F (24°C) | 30 minutes | 2 hours | 2 hours | 6 hours |

Curing time varies with surface temperature, air movement, humidity and film thickness.
- VOLATILE ORGANIC COMPOUNDS**
 - Unthinned:** 0.79 lbs/gallon (94 grams/litre)
 - Thinned 5%:** 0.79 lbs/gallon (94 grams/litre) †
- HAPS**
 - Unthinned:** 0.31 lbs/gal solids
 - Thinned 5%:** 0.31 lbs/gal solids
- THEORETICAL COVERAGE** 643 mil sq ft/gal (15.8 m²/L at 25 microns). See APPLICATION for coverage rates. †
- NUMBER OF COMPONENTS** One
- PACKAGING** 5 gallon (18.9L) pails and 1 gallon (3.79L) cans.
- NET WEIGHT PER GALLON** 10.51 ± 0.25 lbs (4.77 ± .11 kg) †
- STORAGE TEMPERATURE** Minimum 35°F (2°C) Maximum 110°F (43°C)
Protect from freezing.
- TEMPERATURE RESISTANCE** (Dry) Continuous 170°F (77°C) Intermittent 200°F (93°C)
- SHELF LIFE** 12 months at recommended storage temperature.
- FLASH POINT - SETA** N/A
- HEALTH & SAFETY** Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

ENDURATONE® | SERIES 1029

APPLICATION

COVERAGE RATES

| | Dry Mils (Microns) | Wet Mils (Microns) | Sq Ft/Gal (m ² /Gal) |
|-----------|--------------------|--------------------|---------------------------------|
| Suggested | 2.5 (65) | 6.5 (165) | 257 (23.9) |
| Minimum | 2.0 (50) | 5.0 (125) | 321 (29.8) |
| Maximum | 3.0 (75) | 7.5 (190) | 214 (19.9) |

Allow for overspray and surface irregularities. Wet film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. †

MIXING

Stir to uniform consistency without creating air bubbles or foam. Avoid vigorous agitation, boxing or shaking.

THINNING

Thinning is not normally required, but when needed, thin up to 5% or 1/4 pint (190 mL) per gallon with clean tap water.

APPLICATION EQUIPMENT

Air Spray

| Gun | Fluid Tip | Air Cap | Air Hose ID | Mat'l Hose ID | Atomizing Pressure | Pot Pressure |
|---------------|-----------|------------|----------------------------------|----------------------------------|----------------------------|----------------------------|
| DeVilbiss JGA | E | 765 or 704 | 5/16" or 3/8" (7.9 or 9.5 mm) | 3/8" or 1/2" (9.5 or 12.7 mm) | 60-75 psi (4.1-5.2 bar) | 10-20 psi (0.7-1.4 bar) |

Low temperatures or longer hoses require higher pot pressure.

Airless Spray

| Tip Orifice | Atomizing Pressure | Mat'l Hose ID | Manifold Filter |
|------------------------------------|--------------------------------|---------------------------------|--------------------------|
| 0.013"-0.017" (330-430 microns) | 2000-3000 psi (138-207 bar) | 1/4" or 3/8" (6.4 or 9.5 mm) | 60 mesh (250 microns) |

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

Note: On projects involving spray equipment being used over consecutive days, follow Cleanup Instructions below and then leave xylol in the system overnight, flushing thoroughly with clean water before each start-up.

Roller: Use 3/8" (6.4 mm) synthetic woven nap roller cover.

Brush: Use high quality nylon or synthetic bristle brushes.

Note: Floetrol may be used at up to 32 ounces per gallon for improved application properties. Dry-fall and cure properties may be affected. For more information, contact Tnemec Technical Service.

SURFACE TEMPERATURE

Minimum 40°F (4°C) Maximum 120°F (49°C)
The surface should be dry and at least 5°F (3°C) above the dew point.

CLEANUP

Flush and clean all equipment immediately after use with water, then use alcohol or Methyl Ethyl Ketone (MEK) on any dried portions.

CAUTION

Dry overspray can be wiped or washed from most surfaces. Satisfactory dry-fall performance depends upon height of work, weather conditions and equipment adjustment. Low temperature and high humidity are of particular concern. Test for each application as follows: Spray from 15 to 25 feet towards paint container. The material then should readily wipe off. **Note:** Heat can fuse-dry overspray to surfaces. Always clean dry overspray from hot surfaces before fusing occurs. Be aware that exterior surface temperatures can be higher than air temperature.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.